

Stufe	Std.	Min.	Temp.[°C]	C-Pegel	At [mm]	O2	C-Rand [%]
1		00	840	0,800	0,00000	1110	0,17000
1		05	847	0,800	0,00000	1111	0,24936
1		10	855	0,800	0,00000	1113	0,30446
1		15	862	0,800	0,00000	1115	0,34035
1		20	869	0,800	0,00000	1116	0,36298
1		25	877	0,800	0,00000	1118	0,38198
1		30	884	0,800	0,00000	1120	0,40029
1		35	892	0,800	0,00000	1121	0,42041
1		40	900	0,800	0,00000	1123	0,44204
1		45	907	0,800	0,00000	1125	0,46266
1		50	915	0,800	0,02765	1126	0,48656
1		55	922	0,800	0,04195	1128	0,50911
1	1	00	930	0,800	0,05829	1130	0,53411
2	1	00	930	0,800	0,05829	1130	0,53411
2	1	05	930	0,921	0,07440	1139	0,56197
2	1	10	930	1,052	0,09223	1149	0,59763
2	1	15	930	1,194	0,11258	1158	0,64418
2	1	20	930	1,200	0,13218	1159	0,68965
2	1	25	930	1,200	0,15168	1159	0,73209
2	1	30	930	1,200	0,17109	1159	0,77170
2	1	35	930	1,200	0,19011	1159	0,80867
2	1	40	930	1,200	0,20992	1159	0,84574
2	1	45	930	1,200	0,22771	1159	0,87778
2	1	50	930	1,200	0,24534	1159	0,90768
2	1	55	930	1,200	0,26265	1159	0,93559
2	2	00	930	1,200	0,28070	1159	0,96358
2	2	05	930	1,200	0,29713	1159	0,98776
2	2	10	930	1,200	0,31349	1159	1,01034
2	2	15	930	1,200	0,32930	1159	1,03141
2	2	20	930	1,200	0,34499	1159	1,05108
2	2	25	930	1,200	0,36166	1159	1,07080
2	2	30	930	1,200	0,37663	1159	1,08784
2	2	35	930	1,200	0,39173	1159	1,10375
2	2	40	930	1,200	0,40642	1159	1,11860
2	2	45	930	1,200	0,42088	1159	1,13246
2	2	50	930	1,200	0,43642	1159	1,14635
2	2	55	930	1,200	0,45033	1159	1,15836
2	3	00	930	1,200	0,46451	1159	1,16957
2	3	05	930	1,200	0,47821	1159	1,18003
2	3	10	930	1,058	0,49195	1150	1,17874

Stufe	Std.	Min.	Temp.[°C]	C-Pegel	At [mm]	O2	C-Rand [%]
2	3	15	930	1,058	0,50645	1150	1,17753
2	3	20	930	1,058	0,51977	1150	1,17656
2	3	25	930	1,058	0,53297	1150	1,17571
2	3	30	930	1,058	0,54588	1150	1,17497
2	3	35	930	1,058	0,55876	1150	1,17433
2	3	40	930	1,058	0,57220	1150	1,17373
2	3	45	930	1,058	0,58472	1150	1,17325
2	3	50	930	1,058	0,59683	1150	1,17283
2	3	55	930	1,058	0,60892	1150	1,17246
2	4	00	930	1,058	0,62159	1150	1,17212
2	4	05	930	1,058	0,63331	1150	1,17185
2	4	10	930	1,058	0,64475	1150	1,17161
2	4	15	930	1,058	0,65612	1150	1,17140
2	4	20	930	1,058	0,66735	1150	1,17122
2	4	25	930	1,058	0,67919	1150	1,17105
2	4	30	930	1,058	0,69018	1150	1,17092
2	4	35	930	1,058	0,70083	1150	1,17080
2	4	40	930	1,058	0,71166	1150	1,17069
2	4	45	930	1,058	0,72213	1150	1,17061
2	4	50	930	1,058	0,73348	1150	1,17052
2	4	55	930	1,058	0,74379	1150	1,17045
2	5	00	930	1,058	0,75399	1150	1,17040
2	5	05	930	1,058	0,76422	1150	1,17034
2	5	10	930	1,058	0,77417	1150	1,17030
2	5	15	930	1,058	0,78504	1150	1,17026
2	5	20	930	1,058	0,79488	1150	1,17023
2	5	25	930	1,058	0,80467	1150	1,17020
2	5	30	930	1,058	0,81444	1150	1,17017
2	5	35	930	1,058	0,82398	1150	1,17015
2	5	40	930	1,058	0,83441	1150	1,17013
2	5	45	930	1,058	0,84388	1150	1,17011
2	5	50	930	1,058	0,85326	1150	1,17010
2	5	55	930	1,058	0,86272	1150	1,17008
2	6	00	930	1,058	0,87264	1150	1,17007
2	6	05	930	1,058	0,88197	1150	1,17006
2	6	10	930	1,058	0,89117	1150	1,17006
2	6	15	930	1,058	0,90018	1150	1,17005
2	6	20	930	1,058	0,90937	1150	1,17004
2	6	25	930	1,058	0,91905	1150	1,17004
2	6	30	930	1,058	0,92797	1150	1,17003

Stufe	Std.	Min.	Temp.[°C]	C-Pegel	At [mm]	O2	C-Rand [%]
2	6	35	930	1,058	0,93695	1150	1,17003
2	6	40	930	1,058	0,94575	1150	1,17002
2	6	45	930	1,058	0,95456	1150	1,17002
2	6	50	930	1,058	0,96406	1150	1,17002
3	6	55	930	0,678	0,97269	1119	1,11578
3	7	00	930	0,678	0,98142	1119	1,06854
3	7	05	930	0,678	0,99007	1119	1,02741
3	7	10	930	0,678	0,99858	1119	0,99158
3	7	15	930	0,678	1,00785	1119	0,95816
3	7	20	930	0,678	1,01636	1119	0,93128
3	7	25	930	0,678	1,02471	1119	0,90787
3	7	30	930	0,678	1,03324	1119	0,88748
3	7	35	930	0,678	1,04160	1119	0,86973
3	7	40	930	0,678	1,05047	1119	0,85316
3	7	45	930	0,678	1,05882	1119	0,83984
3	7	50	930	0,678	1,06700	1119	0,82824
3	7	55	930	0,678	1,07498	1119	0,81813
3	8	00	930	0,678	1,08372	1119	0,80871
3	8	05	930	0,678	1,09161	1119	0,80113
3	8	10	930	0,678	1,09933	1119	0,79452
3	8	15	930	0,678	1,10706	1119	0,78877
3	8	20	930	0,678	1,11464	1119	0,78377
3	8	25	930	0,678	1,12253	1119	0,77910
3	8	30	930	0,678	1,12984	1119	0,77534
3	8	35	930	0,678	1,13704	1119	0,77207
3	8	40	930	0,678	1,14401	1119	0,76922
3	8	45	930	0,678	1,15083	1119	0,76673
3	8	50	930	0,678	1,15817	1119	0,76442
3	8	55	930	0,678	1,16478	1119	0,76256
3	9	00	930	0,678	1,17122	1119	0,76094
3	9	05	930	0,678	1,17753	1119	0,75952
4	9	10	924	0,678	1,18379	1118	0,75829
4	9	15	918	0,678	1,18942	1116	0,75730
4	9	20	912	0,678	1,19445	1115	0,75649
4	9	25	906	0,678	1,19892	1114	0,75584
4	9	30	899	0,678	1,20339	1112	0,75525
4	9	35	893	0,678	1,20692	1111	0,75482
4	9	40	886	0,678	1,21084	1110	0,75438
4	9	45	881	0,678	1,21382	1108	0,75407
4	9	50	874	0,678	1,21678	1107	0,75377

Stufe	Std.	Min.	Temp.[°C]	C-Pegel	At [mm]	O2	C-Rand [%]
4	9	55	868	0,678	1,21967	1105	0,75350
4	10	00	862	0,678	1,22177	1104	0,75332
4	10	05	856	0,678	1,22423	1103	0,75312
4	10	10	849	0,678	1,22624	1101	0,75296
4	10	15	843	0,678	1,22830	1100	0,75280
4	10	20	837	0,678	1,22994	1099	0,75269
4	10	25	830	0,678	1,23153	1097	0,75257
4	10	30	825	0,678	1,23271	1096	0,75249
4	10	33	820	0,678	1,23352	1095	0,75244